

## HumiSeal<sup>®</sup> 1B73 Acrylic Conformal Coating Technical Data Sheet

HumiSeal<sup>®</sup> 1B73 is a single component, fast drying, acrylic conformal coating intended for use on printed circuit assemblies. HumiSeal<sup>®</sup> 1B73 demonstrates excellent flexibility and electrical properties, fluoresces under UV light for ease of inspection and is easily repaired. HumiSeal<sup>®</sup> 1B73 coating is MIL-I-46058C qualified, IPC-CC-830 and RoHS Directive 2002/95/EC compliant, and recognized under UL File Number E105698.

### Properties of HumiSeal<sup>®</sup> 1B73

Density, per ASTM D1475	0.92 ± 0.02 g/cm <sup>3</sup>
Solids Content, % by weight per Fed-Std-141, Meth. 4044	29.5 ± 2 %
Viscosity, per Fed-Std-141, Meth. 4287	250 ± 20 centipoise
VOC	654 grams/litre
Drying Time to Handle per Fed-Std-141, Meth. 4061	30 minutes
Recommended Coating Thickness	25 - 75 microns
Recommended Curing Conditions	24 hrs @ RT or 2 hrs @ 76°C
Time Required to Reach Optimum Properties	7 days
Recommended Thinner	HumiSeal <sup>®</sup> Thinner 73 HumiSeal <sup>®</sup> Thinner 521EU HumiSeal <sup>®</sup> Stripper 1080
Recommended Stripper	
Shelf Life at Room Temperature, DOM	24 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	67 ppm/°C
Glass Transition Temperature - DSC	42°C
Modulus - DMA	11.1 MPa
Flammability, per UL 94	V-1
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	6300 volts
Dielectric Constant, at 1MHz and 25°C, per ASTM D150-98	2.6
Dissipation Factor, at 1MHz and 25°C, per ASTM D150-98	0.010
Insulation Resistance, per MIL-I-46058C	5.5 x 10 <sup>14</sup> ohms (550TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	7.0 x 10 <sup>10</sup> ohms (70GΩ)
Fungus Resistance, per ASTM G21	Passes

### Application of HumiSeal<sup>®</sup> 1B73

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, flux residues and all other contaminants. Contamination under the coating could cause problems that may lead to assembly failures.

#### Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal<sup>®</sup> 1B73 with HumiSeal<sup>®</sup> Thinner 73 in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal<sup>®</sup> Thinner 73. Viscosity in the dip tank should be checked regularly, using a simple measuring device such as a Zahn or Ford viscosity cup.

## HumiSeal® 1B73 Technical Data Sheet

### Spraying

HumiSeal® 1B73 can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal® Thinner 73 is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of HumiSeal® 1B73 to HumiSeal® Thinner 73 is 1:1 by volume; however the ratio may need to be adjusted to obtain a uniform coating.

### Brushing

HumiSeal® 1B73 may be brushed with a small addition of HumiSeal® Thinner 73. Uniformity of the film depends on component density and operator's technique.

### Storage

HumiSeal® 1B73 should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal® products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

### Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal® Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

## Contact HumiSeal®

### HumiSeal North America

201 Zeta Drive  
Pittsburgh, PA 15238  
USA  
Tel: +1 412-828-1500  
Toll Free (US only): 866-828-5470  
[sales@humiseal.com](mailto:sales@humiseal.com)

### HumiSeal Technical Center

375 University Avenue  
Westwood, MA 02090  
USA  
Tel: +1 781-332-0734  
Fax: +1 781-332-0703  
[techsupport@humiseal.com](mailto:techsupport@humiseal.com)

### HumiSeal Europe

505 Eskdale Road, IQ Winnersh  
Berkshire RG41 5TU  
UK  
Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europesales@chasecorp.com](mailto:europesales@chasecorp.com)

### HumiSeal India

J-154, M.I.D.C Bhosari  
Pune 411 026  
Maharashtra  
India  
Tel: +91 20 66308098  
[indiatechsupport@chasecorp.com](mailto:indiatechsupport@chasecorp.com)

### HumiSeal S.A.R.L

4/6 Avenue Eiffel  
78420 Carrieres-Sur-Seine  
France  
Tel: +33 (0) 1 30 09 86 86  
Fax: +33 (0) 1 30 09 86 87  
[humiseal.sarl@chasecorp.com](mailto:humiseal.sarl@chasecorp.com)

### HumiSeal Asian Support

Tel: 852-9451-6434  
Fax: 852-2413-6289  
[asiatechsupport@humiseal.com](mailto:asiatechsupport@humiseal.com)

### HumiSeal Europe Support

Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europetechsupport@chasecorp.com](mailto:europetechsupport@chasecorp.com)

The information provided herein is for general product selection purposes only. It does not constitute specifications, performance data, or any representation or warranty regarding the product's fit, form, function, merchantability, or fitness for a particular purpose. This information shall not be relied upon for engineering, design, or application decisions.

All responsibility for determining the suitability of the product for any intended use rests solely with the purchaser. The purchaser assumes all risks associated with such use, including compliance with applicable laws, regulations, and standards.

Under no circumstances shall the seller be liable for any loss, damage, cost, expense, or any incidental, indirect, special, punitive, or consequential damages of any kind, including but not limited to lost profits, business interruption, or claims by third parties, arising from or related to the use of, or inability to use, the product, regardless of the legal theory asserted.

No oral or written statements, marketing materials, or other communications shall create or modify any warranty or obligation. The only applicable warranty and terms of sale are those expressly stated in Chase Corporation's official Terms and Conditions of Sale, which exclusively govern all transactions and contain Chase's limited warranty. No other terms, conditions, or representations shall apply.