

HumiSeal® 2E11 Epoxy

Technical Data Sheet

HumiSeal® 2E11 is a room temperature curing two-part epoxy system designed for electronic sealing, encapsulating and potting applications. This product has been formulated with an easy 1:2 volume mix-ratio. HumiSeal 2E11 provides superior adhesion to a wide variety of substrates including most metals and plastics.

APPLICATIONS

- Bonding
- Encapsulating
- Potting

FEATURES

- Easy Mix Ratio
- Extended working time
- Room temperature cure
- Moisture Resistance

SUBSTRATES

- Metals
- Plastics

Properties of HumiSeal® 2E11 Liquids

Chemical Class	Epoxy
Viscosity Part A (25 °C, sp. 7 @ 20 rpm, cps)	11,000 -16,000
Viscosity Part B (25 °C, sp. 6 @ 20 rpm, cps)	5,000 -7,000
Specific Gravity at 25°C (Part A / Part B)	1.16 / 1.00
Color (Part A / Part B)	Clear / Amber
Mix Ratio, PBV (A:B)	1:2
Pot Life @ 25 °C	1 hour
Handling Time @ 25 °C	3 hours
Cure Time @ 25 °C	24-48 hours
Cure Type	2-part reactive epoxy
Curing Conditions	24 hours @ room temp.
Shelf Life, DOM, stored at 18 +/-10 °C	12 months
Cleanup Solvent	Isopropyl alcohol
Color (cured)	Amber
Typical Hardness, Shore D	40
Glass Transition Temperature (Tg)	55 °C
Dielectric Strength, V/mil	500
Dissipation Factor at 1MHz	0.0026
Operating Temperature Range	-45 to 125 °C
Peak Intermittent Temperature	150 °C
Moisture Resistance	Excellent
Water Absorption (1-hour boil)	<1%
Elongation (typical)	90%
Linear Shrinkage (typical)	1%
CTE (ppm, -40 to 80 °C)	65

Storage

HumiSeal® 2E11 Part A and 2E11 Part B should be stored in a cool, dry place between 8°C and 28°C in tightly closed containers. Keep from freezing.

Caution

Application of HumiSeal® 2E11 should be carried out in accordance with local and national health and safety regulations. Use only in well-ventilated areas to avoid inhalation of vapor. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal India

J-154, M.I.D.C Bhosari
Pune 411 026
Maharashtra
India
Tel: +91 20 66308098
indiatechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.