

HumiSeal[®] 2A64 Urethane Conformal Coating Technical Data Sheet

HumiSeal[®] 2A64 is a two component polyurethane conformal coating supplied as Parts A and B, suitable for general printed circuit board applications. HumiSeal[®] 2A64 is characterized by high solids and low viscosity for ease of application and processing, and it fluoresces under UV light for inspection purposes. HumiSeal[®] 2A64 coating is MIL-I-46058C qualified, and IPC-CC-830 and RoHS Directive 2011/65/EC compliant.

Properties of Mixed HumiSeal[®] 2A64

Density, per ASTM D1475	1.07 ± 0.03 g/cm ³
Solids Content, % by weight per Fed-Std-141, Meth. 4044	55 ± 5 %
Viscosity, per Fed-Std-141, Meth. 4287	130 ± 50 centipoise
VOC	501 grams/litre
Recommended Coating Thickness	25 - 75 microns
Drying Time to Handle per Fed-Std-141, Meth. 4061	15 minutes
Curing Condition to Reach Optimum Properties	3 hrs @ 76°C
Recommended Thinner	HumiSeal [®] Thinner 64, Thinner 600
Recommended Stripper	HumiSeal [®] Stripper 1072
Pot Life at Room Temperature	8 hours
Shelf Life at Room Temperature, DOM	12 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	82 ppm/°C (Below T _g) 255 ppm/°C (Above T _g)
Glass Transition Temperature - DSC	12°C
Modulus - DMA	4101 MPa @ -40°C 2777 MPa @ 25°C 2 MPa @ 80°C
Flammability, per MIL-I-46058C	Self-Extinguishing
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	3500 volts
Dielectric Constant, at 1MHz and 25°C per ASTM D150-98	3.5
Dissipation Factor, at 1MHz and 25°C per ASTM D150-98	0.024
Insulation Resistance, per MIL-I-46058C	4.5 x 10 ¹⁴ ohms (450TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	4.8 x 10 ¹⁰ ohms (48GΩ)
Fungus Resistance, per ASTM G21	Passes

Application of HumiSeal[®] 2A64

Cleanliness of the substrate is of extreme importance for the successful application of the coating. Contamination under the coating could cause problems that may lead to assembly failures. For best performance, surfaces should be free of moisture, dirt, wax, grease, flux residues and all other contaminants. If this product will be applied over "no clean" assembly materials, the user should conduct adequate testing to verify compatibility and reliability of the coated assembly.

Mixing ratio of Part A to Part B is 1:1 by volume. Prior to application, HumiSeal[®] 2A64 Parts A and B should be thoroughly mixed until a homogenous blend is achieved. Vigorous mixing is not recommended. The mixed coating should be allowed to settle for 30 minutes prior to use so that any air bubbles formed during blending can escape.

Brushing

HumiSeal[®] 2A64 may be applied by brush. Uniformity of the film depends on component density and operator's technique.

HumiSeal[®] 2A64 Technical Data Sheet

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of prepared HumiSeal[®] 2A64 with a recommended HumiSeal[®] Thinner in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of the recommended HumiSeal[®] Thinner. Viscosity in the dip tank should be checked regularly, using a simple measuring device such as a Zahn or Ford viscosity cup.

Spraying

HumiSeal[®] 2A64 can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of a recommended HumiSeal[®] Thinner is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of prepared HumiSeal[®] 2A64 to HumiSeal[®] Thinner is 1:1 by volume; however, the ratio may need to be adjusted to obtain a uniform coating.

Storage

HumiSeal[®] 2A64 Parts A and B should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal[®] products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

Application of HumiSeal[®] Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal[®] Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

375 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal India

J-154, M.I.D.C Bhosari
Pune 411 026
Maharashtra
India
Tel: +91 20 66308098
indiatechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.