



Tapecoat®

Technical Data Sheet

DESCRIPTION

Tapecoat TC® 7000 Epoxy is a two part, 100% solids, high temperature coating designed to provide protection against corrosion on pipelines with service temperatures up to 300°F (149°C). TC 7000 can be used as an above or below grade standalone coating or as a primer for Tapecoat high temperature tape products. In above grade applications oxidation is expected, but at the recommended coating thickness long term protection will be provided. TC 7000 is a fast curing epoxy allowing for backfill in 2-3 hours at 70°F and 50% RH.

SUBSTRATE COMPATIBILITY

Steel, Stainless Steel, Ductile Iron, other metals, FBE

RECOMMENDED USE

Ideal for protecting girth welds, fittings, flanges, valves, and all types of piping and metal structures. Can also be used for directional drilling when reinforced with TC Reinforcing Scrim.

SURFACE PREPARATION

SSPC SP-10/NACE No. 2/ SA 2 1/2 Near-White Blast Cleaning
2-4 mil surface profile

PRIMER

None Required

OPTIONAL REINFORCEMENT

To increase abrasion and impact resistance and for creating high coating build TC Reinforcing Scrim can be used.

REFERENCE

TC 7000 meets all of the performance criteria listed in the most recent revisions of:

NACE RP0105
ANSI/AWWA C210

SAFETY

Refer to Material Safety Data Sheet: MSDS-TC7000-RESIN; MSDS-TC7000-HARDENER

APPLICATION

Refer to Application Guidelines: AG-EPOXIES

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.

Chase Corporation
375 University Avenue
Westwood, MA 02090

Phone: 800-323-4182
Fax: 781-332-0701
www.chasecorp.com

An ISO 9001:2015
REGISTERED COMPANY

TYPICAL DATA

Property	US Customary	Metric	Test Method
Color	Red	Red	
Coating Thickness			
As a Stand Alone Coating	25 mil	635 μm	
As a Primer	6-10 mil	150-250 μm	
VOC Content	0 lb/gal	0 g/l	
Pot Life @ 70° F (21° C), 50% RH	15-20 minutes	15-20 minutes	
Time to Backfill @ 70° F (21° C), 50% RH	2-3 Hours	2-3 Hours	
Cathodic Disbondment, 30 days	<0.1 in ²	<2 mm radial	ASTM G8
Cathodic Disbondment, 250° F (121° C), 30 days, Tapecoat 7000	<0.4 in ²	<10 mm radial	ASTM G42 (modified for internal heating)
Pull Off Adhesion to Steel	>2000 psi	> 13.8 MPa	ASTM D4541 Type II
Pull Off Adhesion to FBE	>2000 psi	> 13.8 MPa	ASTM D4541 Type II
Impact Resistance	22 in*lb	2.5J	ASTM G14
Shore D Hardness	85-90	85-90	ASTM D2240
Dielectric Strength	Exceeds 12 kV (25 mil)	Exceeds 12 KV (635 μm)	ASTM D149
Holiday Detection Setting	6250 V (25 mil)	6250 V (635 μm)	NACE RP0274
Water Absorption	<0.5%	<0.5%	ASTM D570
Water Vapor Transmission Rate	<0.01 g/(24h*100 in ²) (25 mil)	<0.05 g/(h*m ²) (635 μm)	ASTM E96 Procedure B
Chemical Resistance	Pass	Pass	ASTM G20
Application Temperature Range	45° F to 120° F	7° C to 49° C	
Service Temperature Range	40° F to 300° F	4° C to 149° C	

ORDERING INFORMATION

TC 7000

Kit Size	Kits Per Case	Lbs. Per Case
Quart	4	10.6
Gallon	4	42.4

TC REINFORCING SCRIM

Roll Size	Rolls Per Case	Lbs. Per Case
2" x 100'	24	10
4" x 100'	12	10
6" x 100'	8	10